

Using a Nuclear Elemental Static Sample Analyzer to Optimize the Operation of a Preparation Plant

Steve Foster

Vice President Product Development; SABIA, Inc.

Abstract

A large coal preparation plant in West Virginia is using a SABIA Model L-2000 to analyze the ash levels in product as it leaves the plant in order to adjust the circuits in real time and optimize the plant output. Operating at nearly 4M tons of coal per year the site delivers both steam and metallurgical coal to customers in the United States and around the world. The static sample analyzer, which delivers a sulfur and ash analysis in 15 minutes or less on one-gallon samples is being used to give the customer a quicker turn around on prep plant adjustments as the coal ash levels vary coming out of the prep plant. This paper takes a look at both the economics as well as application details and the difference this analyzer could make for the operation.

** Nuclear Elemental Analyzers as defined for the purposes of this paper includes those analyzers that measure the individual elements of the periodic table. For example, Ash is determined by adding the sum of the individually measured constituents of Ash, i.e., Silicon, Iron, Calcium, Aluminum, Potassium, Titanium, etc...

Introduction

What is a static sample analyzer?

How they work

The installation and application

Using the data

Some Do's and Don'ts

Looking ahead

Summary

Introduction

The coal company has multiple modern mining complexes located in southern West Virginia, eastern Kentucky and southern Virginia, utilizing underground room and pillar mining as well as underground longwall and surface and highwall mining. These mining systems include hundreds of miles of belt structure. These operations sell high-quality, low sulfur coal for electric generation, steel making and industrial application. Overall the company has over a dozen state-of-the-art preparation plants, processing raw coal at a combined rated capacity nearly 20,000 tons per hour.

The processing plant operates at nearly 4M tons of coal per year. The site delivers both steam and metallurgical coal to customers in the United States and around the world. The static sample analyzer, which delivers a sulfur and ash analysis measurement in 15 minutes or less on one-gallon samples is being used to give the customer a quicker turn around on prep plant adjustments as the coal ash levels vary coming out of the prep plant.

What is a Static Sample Analyzer?

As a result of the pioneering work of Bob Stewart at the Bureau of Mines in the 1970's and further research under grants from the federal government and from EPRI in the 1970's and 1980's it became possible to introduce a commercially viable nuclear elemental analyzer in the mid-1980's. The technology uses a technique known as prompt gamma neutron activation (PGNA). In this process a spontaneous fissioning nuclear source such as Californium 252 is used to bombard a sample to be analyzed with massive quantities of neutrons – several hundred thousand per second. In turn, the elemental atoms in the sample capture a large number of the incident neutrons. These atoms become unstable but quickly re-stabilize by emitting an array of gamma energies. Since each element emits a unique set of gamma energies, spectral analysis identifies which elements are in the material. As a true elemental analysis technology, it can measure on-line and in real time the quantities Silicon, Calcium Aluminum, Iron, Titanium, Magnesium, Potassium, Sodium, and Sulfur, as well as Chlorine, Nitrogen, and Hydrogen.

The first successful version of these instruments was “chute-type” analyzers that required a gravity-feed of the producer's crushed quarry materials from the top of the unit onto an exit conveyor underneath the unit and now is available as a laboratory instrument that quickly gives sulfur, ash, moisture, BTU and SO₂ in 15 minutes with no sample preparation. A lab version of the technology is shown below:



Figure 1. The Static Sample Analyzer

In this model the sample is placed in a 1-gallon pitcher, the kind available at the local Wal-Mart, and then the pitcher is placed in the drawer for insertion into the nuclear analyzers. The operator presses a button on the analyzer display keyboard and the analysis process begins with results appearing in 10 to 15 minutes.

How They Work

Basic Principles

When a bulk material such as cement is bombarded with thermal neutrons, (<1 electron volt neutron energy), from a Californium 252 nuclear source, many of the neutrons are captured by elemental atoms within the cement. When this happens the atom becomes temporarily unstable. In order to re-stabilize the atom sheds a spectrum of high-energy gamma rays. The specific energies of gamma rays given off are a unique set for each of the elements within the periodic table. This principle makes it possible to create a signal to enable the on-line elemental analysis of cement possible with PGNA.

Obtaining and Processing the Signal

In order to create an electronic signal used for the determination of the weight percent of the elements of interest within the cement the unique elemental signature gamma rays resulting from the capture of neutrons by elemental atoms are detected by a scintillating crystal such as Sodium Iodide (NaI). As the gamma rays penetrate the detector they deposit their energy as high-speed electrons within the crystal. These electrons create ionization, which can be detected as UV light pulses. The light pulses are in turn detected by photo-multiplier tubes (a vacuum tube electronic component operating at a high voltage, typically 500 to 1000 VDC) and turned into electrical pulses which are immediately amplified, shaped and then converted into digital signals, and collected into a spectrum over some predetermined period of time (typically one minute) which can then be processed by a computer at very high speeds.




Figure 2. The Nuclear Physics of PGNAA

Processing the Spectrum

The resulting gamma-ray spectrum collected over a one-minute period is actually a distribution of all the incoming gamma-ray energy levels ranging from zero to ten Mev (Million electron volts). In cement applications anywhere from five to fifteen elements of interest are represented in the spectrum. A typical spectrum is shown below which over in one minute collects several million pulses.

Typical PGNAA Gamma-Ray Spectra




Figure 3. A Typical Gamma Ray Spectrum – High and Low Energies

Typical PGNAA Gamma-Ray Spectra




Figure 4. A Typical Gamma Ray High Energy Spectrum

Intuition says that arriving at the weight percent of each element could be accomplished with a simple evaluation of the size of each of the peaks, which is not the case. The MLR approach takes into account the entire shape of all the elemental peaks. Most commonly, vendors use a full-spectrum analysis such as Library Least Squares that utilizes the instrument response to pure elements used as a library against which the incoming spectral data can be compared on a minute-by-minute basis. Typically a multiple linear regression technique is used which solves a linear matrix equation with matrix inverse math. With the high speed and data capacity of computers available today, the time required for this mathematical treatment (de-convolution of the spectra) of the data takes only seconds and becomes transparent to the end user. Prior to presentation of the final answers to the cement producer, the results of the multiple linear- regression are normalized with respect to each other. The technology has made significant strides and now offers the marketplace impressive precisions and accuracies. **Today's analyzers calibrated in the factory with an orthogonal set of synthetic coal reference standards arrive at the site calibrated for the universe of possibilities in coal.** This means that the analyzers can be immune to changes in raw-material types.

The technology is highly accurate, with accuracies of 0.05% for sulfur and 0.50% for ash. Below is a table of sensitivities for many of the elements in the periodic table:

Table 1. Expected PGNA Sensitivity to Elements of Interest*	
Sensitivity in Weight % **	Elements
<0.01%	Cl, Sc, Ti, Ni, Cd, Hg, Sm, Gd, Dy, Ho
0.01-0.1%	S, V, Cr, Mn, Fe, Co, Cu, Rh, Ag, In, Hf, Ir, Au, Nd, Eu, Er, Yb, H
0.1-0.3%	N, Na, Al, Si, K, Ca, Ga, Se, Y, Cs, La, W, Re, Os, Pt, Pr, Tm
0.3-1.0%	Li, Be, Mg, P, Zn, As, Mo, Te, I, Ta, Pb, Ce, Tb, Lu, Th, U
1.0-3.0%	C, Ge, Br, Sr, Zr, Ru, Pd, Sb, Tl
>3.0%	Other Elements
* Note: Table taken from "On-Line Prompt Gamma Neutron Activation Analyzers, Published in the Process/Industrial Instrument and Controls Handbook, Editor-Gregory K. McMillan, Fifth Edition, McGraw Hill, 1999.	
** Three sigma detection limit in 10 minutes within an elementary simple rock matrix, ≥150mm thick	

Figure 5. PGNAA Sensitivity




Figure 6. PGNAA Timeline

Screenshots

Below are snapshots of some of the more commonly used screens on the Quicklab:

The screenshot shows a Mozilla browser window displaying the SABIA Processing Static Analyzer interface. The browser's address bar shows the URL `http://192.168.1.250/staticFramesStart.php`. The page title is "Processing Static Analyzer".

At the top right, the status indicates "03/30/06 06:32:42pm: performing analysis". Below this, a message says "Please wait for the results section to update". A list of timestamps follows, all marked as "analysis complete":

- 03/30/06 06:32:37pm: analysis complete
- 03/30/06 06:32:26pm: analysis complete
- 03/30/06 06:32:14pm: analysis complete
- 03/30/06 06:32:03pm: analysis complete
- 03/30/06 06:31:51pm: analysis complete
- 03/30/06 06:31:40pm: analysis complete

On the left side, there is a navigation menu with buttons for "New Sample", "Recent Samples", "Older Samples", "Historical Data", "Current Data", "Extended Results", and "System Status". The "Current Data" button is highlighted.

The main content area is titled "Current Data" and shows "All Percent Avg: from 2006-03-30 18:17:00 to 2006-03-30 18:32:00 (15m)". Below this is a table:

Item	%
Moisture	0.00
Ash	50.00
Sulfur	6.00

Below the table is a "File Name" input field and an "Export" button.

The section "Raw Elemental Analysis" contains a table with the following data:

Analysis Time	Span	Valid	Counts/sec	Counts/sec above thresh	ChiSquare
30Mar2006 18:32:00	900	900	400,109	48,241	0.90

Below this table is another table with the following data:

Element	Coeff Raw	Sigma %	Corr	Area %
detector	1.5258	0.278	0.99	116.42
sulfur	2.3774	15.402	0.79	0.26
silicon	3.2299	3.817	0.91	1.39
iron	0.1176	4.433	0.54	0.70
calcium	0.0785	4.928	0.79	1.89
aluminum	0.1022	10.616	0.69	-0.44
carbon	-170,375.8170	0.915	0.73	-5.00
chlorine	0.0443	5.074	0.81	1.12
titanium	0.0562	4.912	0.72	1.66

At the bottom left, "External IO:" information is displayed: "Thu Mar 30 18:29:59 2006" and "Detector Temp 40 C". The browser's status bar at the bottom shows "Waiting for 192.168.1.250..."

Figure 7. Main User Screen with Analysis Results

SABIA Massey Liberty Processing Static Analyzer Main Page - Mozilla



Processing Static Analyzer

S1 Software versions Analyzer: 1.7-17

Start New Sample Analysis

Operator ID	<input type="text"/>
Sample ID <i>Sample ID must not be "IDLE" or blank</i>	<input type="text"/>
Sample Origin	<input type="text"/>
Area	<input type="text"/>
Pit	<input type="text"/>
Seam	<input type="text"/>
Split	<input type="text"/>
Other1	<input type="text"/>
Other2	<input type="text"/>
Weight	<input type="text"/>
Destination	<input type="text"/>
Tons	<input type="text"/>
Tag Time Span (#h #m #s)	<input type="text" value="15m"/>

Analyze Sample

Unset All Tags

Figure 8. Starting a new sample – the user types in ID and then selects from predefined pull down menus for additional descriptive information

Mozilla
 File Edit View Go Bookmarks Tools Window Help
 http://192.168.1.250/staticFramesStart.php
 Home Bookmarks mozilla.org mozillaZine mozdev.org

SABIA Processing Static Analyzer
 Analyzer Status: OK Time: 03/30/06 18:28:47 PST

03/30/06 06:28:42pm: analysis complete
 03/30/06 06:28:38pm: analysis complete
 03/30/06 06:28:19pm: analysis complete
 03/30/06 06:28:15pm: analysis complete
 03/30/06 06:27:55pm: analysis complete
 03/30/06 06:27:52pm: analysis complete
 03/30/06 06:27:31pm: analysis complete
 03/30/06 06:27:29pm: analysis complete
 03/30/06 06:27:07pm: analysis complete
 03/30/06 06:27:06pm: analysis complete

System Status and Settings
This screen refreshes every 30 seconds

System Time	30 Mar 2006 18:28:51 PST
Datad State	
PLCDD State	plcd not installed
	datad1
Response Set	massey_static_coal
Alignment Set	massey_static_coal
Counts Per Sec.	400,044
	<i>Current Alignment Status</i>
Alignment	Aligned
Good Data Secs.	60
Counts	24,002,700
H FWHM	5.28
H Peak	99.47
Alignment Gain	0.99
Alignment Offset	1.12
PMT Active Control	Fine-Track
PMT Active State	LOCKED
	<i>System Parameters</i>
Free Disk Space	168,786MB 90.96%
	Ok Controller: c0

External IO:
 Thu Mar 30 18:29:59 2006
 Detector Temp 40 C

New Sample
 Recent Samples
 Older Samples
 Historical Data
 Current Data
 Extended Results
 System Status

Done

Figure 9. Checking the System Status Screen

Mozilla <2>

File Edit View Go Bookmarks Tools Window Help

Back Forward Reload Stop Print



Analyzer Status Time
OK 03/30/06 18:29:12 PST

Current sample summary update age 00:17

Sample Rolling History over last 48h

Click [here](#) for export to MS Excel

Start Time	Duration	Operator ID	Sample ID	Sample Origin	Area	Pit	Seam	Split	Other1	Other2	Weight	Destination	Tons	Moisture	Ash	Sulfur
03-30-06 05:32:41	16m10s	hs	16284								3.08kg			7.75	50	6
03-30-06 04:13:51	16m10s	hs	16283								3.21kg			6.99	50	6
03-30-06 02:43:31	17m20s	hs	16282								3.51kg			7.57	50	6
03-30-06 01:53:31	17m10s	hs	16281								3.03kg			7.64	50	6
03-30-06 01:13:21	17m10s	hs	16280								3.14kg			6.32	50	6
03-29-06 10:12:31	17m10s	gjl	16278								2.83kg			6.05	50	6
03-29-06 09:27:41	16m10s	gjl	16277								2.70kg			6.80	50	6
03-29-06 08:52:31	17m20s	gjl	16276								2.81kg			6.86	50	6
03-29-06 07:59:21	17m10s	gjl	16275								2.70kg			5.98	50	6
03-29-06 06:38:41	16m10s	hs	16274								3.31kg			7.25	50	6
03-29-06 04:14:41	16m10s	hs	16273								3.41kg			7.44	50	6
03-28-06 23:54:32	17m20s	hs	16271								3.62kg			7.35	50	6
03-28-06 23:25:52	16m10s	hs	16271								3.36kg			7.35	50	6
03-28-06 21:51:42	16m10s	hs	16270								3.11kg			8.18	50	6
03-28-06 21:19:02	16m20s	hs	16269								3.05kg			8.08	50	6
03-28-06 20:38:22	17m20s	hs	16268								3.34			7.87	50	6

File Name Export

Figure 10. Sample Summary Screen shows summary of recently run samples

Mozilla
File Edit View Go Bookmarks Tools Window Help
Back Forward Reload Stop
http://192.168.1.250/staticFramesStart.php
Home Bookmarks mozilla.org mozillaZine mozdev.org

SABIA Processing Static Analyzer
Analyzer Status: OK Time: 03/30/06 18:30:52 PST

03/30/06 06:30:50pm: pls. wait
03/30/06 06:30:40pm: analysis complete
03/30/06 06:30:32pm: analysis complete
03/30/06 06:30:17pm: analysis complete
03/30/06 06:30:09pm: analysis complete
03/30/06 06:29:53pm: analysis complete
03/30/06 06:29:46pm: analysis complete
03/30/06 06:29:30pm: analysis complete
03/30/06 06:29:23pm: analysis complete
03/30/06 06:29:06pm: analysis complete

List of Records
Records from 03-30-06 18:03:51 to 03-30-06 18:03:51

Sample ID	Record Date	Duration	Span	Bulk Avg.
IDLE	03-30-06 05:48:51	12h42m	12h42m	12h42m
16284	03-30-06 05:32:41	16m10s	16m10s	16m10s
IDLE	03-30-06 04:30:01	1h2m40s	1h2m40s	1h2m40s
16283	03-30-06 04:13:51	16m10s	16m10s	16m10s
IDLE	03-30-06 03:00:51	1h13m	1h13m	1h13m
16282	03-30-06 02:43:31	17m20s	17m20s	17m20s
IDLE	03-30-06 02:10:41	32m50s	32m50s	32m50s
16281	03-30-06 01:53:31	17m10s	17m10s	17m10s
IDLE	03-30-06 01:30:31	23m	23m	23m
16280	03-30-06 01:13:21	17m10s	17m10s	17m10s
IDLE	03-29-06 10:29:41	14h43m40s	14h43m40s	14h43m40s
16278	03-29-06 10:12:31	17m10s	17m10s	17m10s
IDLE	03-29-06 09:43:51	28m40s	28m40s	28m40s
16277	03-29-06 09:27:41	16m10s	16m10s	16m10s
IDLE	03-29-06 09:09:51	17m50s	17m50s	17m50s
16276	03-29-06 08:52:31	17m20s	17m20s	17m20s
IDLE	03-29-06 08:16:31	36m	36m	36m
16275	03-29-06 07:59:21	17m10s	17m10s	17m10s
IDLE	03-29-06 06:54:51	1h4m30s	1h4m30s	1h4m30s
16274	03-29-06 06:38:41	16m10s	16m10s	16m10s
IDLE	03-29-06 04:30:51	2h7m50s	2h7m50s	2h7m50s

External IO:
Thu Mar 30 18:29:59 2006
Detector Temp 40 C

New Sample
Recent Samples
Older Samples
Historical Data
Current Data
Extended Results
System Status

Done

Figure 11. The Historical Screen allows user to review any past sample run




Figure 12 Looking at the spectrum

The Installation and Application

At the prep plant ash ranges from 10% to 16% and sulfur from 0.7% to 0.9%. A two-stage sweep arm sampler is utilized to obtain ongoing samples of clean coal product as it exits the prep plant. Historically this coal has been crushed to 8 mesh and riffled for analysis in the on-site lab. As is typical for a conventional lab it takes about 2 hours to obtain a quick ash result and 4 hours to get an ASTM ash. With the experience and extra care taken by the lab personnel at the site their quick ash readings are often within 0.1% of the ASTM lab ash readings. These quick ash readings are used to keep the prep plant in adjustment, minimizing production costs and ensuring that outgoing product meets customer specifications, but of course the 2 hour delay from sample to analysis severely minimizes the effectiveness of the process control.

Using the Data

With the implementation of a nuclear static sample analyzer the operation is now able to get accurate ash results in a fraction of the time with conventional lab techniques. Initially lab personnel will be using the static analyzer results to decide if adjustments to the plant ash cleaning circuits are necessary. With time and experience, using results from samples every 15 minutes, it is expected that significant progress will be made in optimizing the plant operation. Below are graphs of initial calibration results:

Accuracy




Figure 13. Quicklab Sulfur Performance




Figure 14 Quicklab AshPerformance

Repeatability

Calibrated Results for Repeated Runs of a single coal sample			
15 minute run time			
Sample #	Ash wt%	Sulfur wt%	
1	5.91	0.78	
2	6.63	0.78	
3	6.54	0.78	
4	6.02	0.78	
5	6.53	0.78	
6	6.64	0.78	
7	6.67	0.78	
8	5.81	0.78	
9	6.12	0.78	
10	5.92	0.78	
11	5.85	0.78	
12	6.32	0.78	
13	6.12	0.78	
14	5.88	0.78	
std. dev =	0.331	0.000	

Figure 15 Quicklab Repeatability

Some Do's and Don'ts

Do

- Ensure samples are truly representative of the process
- Vendor and customer conduct site survey early in project
- Pay attention to installation details
- Educate analyzer users in safety of device
- Make certain remote hookup between vendor and analyzer is available

Don't

- Underestimate data communication issues
- Underestimate time to license nuclear sources

Looking Ahead

To further utilize the information from the analyzer the customer will be monitoring the iron results in the content of the samples. It is hoped that the timeliness of the analyzer results can enable the operators to not only keep the ash level of the coal output from the prep plant more consistent but also enable the plant operators to minimize the loss of magnetite in coal leaving the prep plant. It is estimated that a typical large coal cleaning operation spends as much as \$100K per month on magnetite. A 10% reduction in this expense by keeping the circuits in better adjustment could potentially pay for the analyzer over the course of a year.

Summary

It is still early in the operation's journey to use cutting edge technology to optimize operation, reduce costs and maximize profitability, but the experience so far with PGNA has proven beneficial. The site has correctly identified the culprit in achieving optimum quality and profitability as variation and they are well on their way to significantly reducing variation in the output of the prep plant.

REFERENCES

Foster, Stephen, "What is involved in Effective Calibration of a PGNA Analyzer in the Factory and the Field", International On-Line Coal Analyzer Technical Conference, St. Louis, MO, November, 2004.

Proctor, R.J., "On-line Prompt Gamma Neutron Activation Analyzers", Process/Industrial and Controls Handbook, Editor-Gregory K. McMillan, Fifth Edition, McGraw Hill, 1999.

Sanda, Arthur P., "On-line Analyzers Improve Coal Quality", Coal Age Magazine, p.52, June 1992.

Snider, Kurt, Woodward, Richard. "Using an On-Line Elemental Coal Analyzer to Reduce Lost Generation Due to Slagging", International On-line Coal Analyzer Technical Conference, St.Louis, MO, November 2004.